IMPILO industries

TECHNICAL DATA SHEET

SC 50 BUTYL | STEAM CURE SOLID MATERIAL BASED ON BROMO BUTYL SYNTHETIC RUBBER

SC 50 BUTYL is a premium grade, steam cure 50 Shore A Hardness Bromo Butyl Synthetic Rubber, used in acid, chemical and demineralization water applications.

PRODUCT OVERVIEW

- Typical applications include lining of tanks, launders, pipes, and chutes,
- Not suited for abrasion and high wear applications.



STANDARD FEATURES

01 **Roll Width:** 1200mm–1450mm wide (custom on request)

02 **Thickness Range:** 1.5mm–20.0mm

03 **Length Range:** 10 or 12m (custom on request)

04 **Available Colours:** Black

05 **Packaging:** Yellow Embossed Plastic



RECOMMENDED STORAGE CONDITIONS:
Store below **23°C** on **suspended** racks or shelving to avoid **creasing, damage, and flat spots.**
Typical **values may vary** by batch **and** application and are **not a performance guarantee.**
Users must confirm material suitability before use.

PHYSICAL PROPERTIES

DESCRIPTION	BROMO BUTYL (BIIR)
Hardness (SANS 10048)	50±5 Shore A
Specific Gravity (S.G)	1.17 (±0.2) g/cm³
Elongation At Break (SANS 10037)	500% (min)
Tensile Strength (SANS 10037)	7 Mpa (min)
Classification (SANS 1198-2005)	Type 2 Grade C Class 50
Tear Strength (ISO 34:2022)	N/A
Abrasion Loss (ISO Method B)	N/A
Temperature Range	Minus 40°C to 120°C
Shelf Life @23°C	6 weeks from manufacture date

MATERIALS TESTING
STANDARD TESTING INCLUDES:
✓ Rheometer & SG Testing
✓ E@B Testing
✓ Tensile Testing
✓ Mooney Viscosity
OPTIONAL TESTING ON REQUEST:
✓ Abrasion Resistance
✓ Compression Set
✓ Rebound Resilience

ADHESION SYSTEM

NON-UV RESISTANT

Uncured Rubber to Metal

- HeroBond®080 (Orange Primer) 10-11m2
  Minimum drying time 30 minutes
- HeroBond®082 (Black cover coat) 9-10m2
  Minimum drying time 30 minutes at room temperature
- HeroBond®086 (Black tie coat)
  1 coat 6,2 sq.m/litre 2 coats 3,1 sq.m/litre
  One coat on steel, one coat on rubber

UV RESISTANT

- HeroBond®089 Green Primer 11m2
  1 hour to dry in-between
- HeroBond®090 Red Cover Coat 20m2



NOTE:

- The handling precautions above are limited to general recommendations based on information obtained from suppliers of individual compounding ingredients.
- Information is given with the understanding that the manufacturer will satisfy themselves that precautions to health and safety hazards presented by their conditions of use are adequate.
- Since conditions of product and disposal is outside our control we make no warranties, express or implied, and assume no liability in connection with any use of this information.

Revised 28 August 2026

Rubber On The Roll

www.impilogroup.com
admin@impilogroup.co.za
5 Berry Road, Roodekop, Germiston, 1491
+27 (11) 465 9840